

Lithium Iron Phosphate (LiFePO4) Battery XZOWIE-12200M (12.8V200Ah)

Features Of LiFePO4 Battery

Longer Cycle Life: Offers up to 20 times longer cycle life and five times longer float/calendar life than lead acid battery, helping to minimize replacement cost and reduce total cost of ownership.


Lighter Weight: About 40% of the weight of a comparable lead acid battery. A 'drop in' replacement for lead acid batteries.

Higher Power: Delivers twice power of lead acid battery, even high discharge rate, while maintaining high energy capacity.

Wider Temperature Range: -20°C~60°C.

Superior Safety: Lithium Iron Phosphate chemistry eliminates the risk of explosion or combustion due to high impact, overcharging or short circuit situation.

Physical Dimension-mm









Typical Applications

- Wheelchairs and scooters
- Solar/wind energy storage
- Back-up power for small UPS
- Golf trolleys & buggies
- Electric bikes
- Tools

Specification

	T.,	10.017
	Nominal Voltage	12.8V
	Nominal Capacity	200Ah
	Energy	2560Wh
Electrical	Internal Resistance(AC)	≤20mΩ
Characteristics	Cycle Life	>3000 cycles @0.5C 80%DOD
	Months Self Discharge	<3%
	Efficiency of Charge	100% @0.5C
	Efficiency of Discharge	96~99% @1C
Standard Charge	Charge Voltage	14.6±0.2V
	Charge Mode	0.2C to 14.6V, then 14.6V, charge current to 0.02C (CC/CV)
	Charge Current	60A
	Max. Charge Current	120A
	Charge Cut-off Voltage	14.6V±0.2V
Standard Discharge	Rated Discharge Current	60A
	Max. Discharge Current	120A
	Discharge Cut-off Voltage	10V
Environmental	Charge Temperature	0 $^{\circ}$ C to 55 $^{\circ}$ C (32F to 131F) $@60\pm25\%$ Relative Humidity
	Discharge Temperature	−20 $^{\circ}$ C to 60 $^{\circ}$ C (−4F to 140F) $@60\pm25\%$ Relative Humidity
	Storage Temperature	$^-$ 20 $^\circ$ C to 45 $^\circ$ C (-4F to 113F) $^\circ$ @60 \pm 25% Relative Humidity
	IP Class	IP65
Mechanical	Plastic Case	ABS
	Approx. Dimensions	522mm*240mm*224mm (20.55in.*9.45in.*8.82in.)
	Approx. Weight	24.20kg (53.80lbs)
	Terminal	M8






Lithium Iron Phosphate (LiFePO4) Battery XZOWIE-12200M (12.8V200Ah)


Different Rate Discharge Curve(25℃)

14.0 13.2 12.4 10.0 10.0 9.2 0.5c 0.5c


Different Temperature Discharge Curve(0.5C)




State of Charge Curve(0.5C, 25℃)




Charging Characteristics(0.5C, 25°C)



Different DOD Discharge Cycle Life Curve(0.5C)



Different Temperature Self Discharge Curve



Publication No :XZOWIE-12200M-PD-EN-V2.0-202208



Http://:www.xzowie.com zhuoweixinnengyuan@163.com

Henan Zhuowei New Energy Technology Co., Ltd Add:Beihuan Battery Industrial Park, Xinxiang City, Henan Province

